

Calcined Alumina/Kalzinierte Tonerde Aluminium oxide/Aluminiumoxid

Type: **SALOX[®] MS15 (GKT-MS)**

Main application: Production of refractory materials and alumina cements
Hauptinsatzgebiet: Herstellung von feuerfesten Materialien und Tonerdezement

Chemical characteristics/Chemische Eigenschaften [%]			
	Typical/Typisch	Min.	Max.
Al ₂ O ₃	99.7	99.3	
SiO ₂	0.03		0.05
Fe ₂ O ₃	0.025		0.05
Na ₂ O (TOTAL / GESAMT)	0.18		0.20
CaO	0.04		0.06

Physical characteristics/Physikalische Eigenschaften		Typical/Typisch
Specific surface area (BET)/Spezifische Oberfläche (BET)	[m ² /g]	3 - 10
Bulk density/Schüttgewicht	[kg/m ³]	950
Average particle size d ₅₀ /Durchschnittliche Korngröße d ₅₀	[µm]	55 - 85
+63 µm sieve / +63 µm Sieb	[%]	20 - 50

Standard packing/Standard Verpackung

- Big Bags: 1 mt, 1.5 mt, 2 mt