

Zeolite Activated Granulate Zeolithe aktivierte Granulate

Type: **Asorbio[®] ZAG-3A**

Main application: Adsorption of water vapor
Haupt Einsatzgebiet: Adsorption von Wasserdampf

| Chemical characteristics/Chemische Eigenschaften [%] | Typical/Typisch | |
|--|-----------------|-----|
| Zeolite 3A/Zeolith 3A | 80 | ± 3 |
| Binder | 18 | ± 2 |
| Water/Wasser | 2 | ± 1 |

| Physical characteristics/Physikalische Eigenschaften | Typical/Typisch | |
|---|-----------------|------|
| Bulk density/Schüttgewicht [g/l] | 730 | ± 70 |
| Static water adsorption/Statische Wasseradsorption (25 °C, RH=55 %, 24 h) [%] | 22 | ± 3 |

| Standard granulations | | | | |
|---|------|-----------|-----------|-----------|
| Typical particle size Partikelgrößenverteilung | [mm] | 1.6 - 2.5 | 2.0 - 3.6 | 3.0 - 5.0 |
| Hardness/Härte | [N] | 20 ± 10 | 40 ± 20 | 60 ± 20 |

Standard packing/Standard Verpackung

- Plastic Bags: 25 kg/Pallet 1 mt
- Metal Drums: 140 kg
- Big Bags: 0.5 mt or 1 mt

Rev: 01 - 18

