

# Zeolite Activated Granulate Zeolithe aktivierte Granulate

Type: **Asorbio<sup>®</sup> ZAG-MFI**

Main application: Adsorption of organic vapor  
Haupt Einsatzgebiet: Adsorption von organischen Dämpfen

Chemical characteristics/Chemische Eigenschaften [%]	Typical/Typisch	
Zeolite silicate	80	± 3
Binder	18	± 1
Water/Wasser	1.5	± 1

Physical characteristics/Physikalische Eigenschaften	Typical/Typisch	
Bulk density/Schüttgewicht [g/l]	770	± 50
Static water adsorption/Statische Wasseradsorption (25 °C, RH=55 %, 24 h) [%]	max. 2.5	

Standard granulations				
Typical particle size Partikelgrößenverteilung	[mm]	1.6 - 2.5	2.0 - 3.6	3.0 - 5.0
Hardness/Härte	[N]	20 ± 10	40 ± 20	60 ± 20

### Standard packing/Standard Verpackung

- Plastic Bags: 25 kg/Pallet 1 mt
- Metal Drums: 140 kg
- Big Bags: 0.5 mt or 1 mt

Rev: 01 - 18

